

In the claims:

Please amend the claims as shown below:

1. (Currently amended) A method for the treatment of chips,  
5 comprising:  
heating the chips with steam in a steam treatment inside a  
steam treatment vessel,  
directly adding an acidic fluid to the chips disposed in the  
steam treatment vessel while the chips being steamed in the  
10 steam treatment vessel ~~during the steam treatment~~ in an amount  
that gives the chips at least a five-fold increase in an ionic  
concentration of hydrogen ions at an end of the steam  
treatment compared to steam treatment without adding the  
acidic fluid,  
15 reducing a final pH of the chips by at least 0.5 units,  
forming the chips to a slurry with an alkali impregnation  
fluid,  
conveying the slurry to a digester, and  
cooking the chips in the digester.
- 20
2. (Previously presented) The method according to claim 1  
wherein the acidic fluid has a pH that does not exceed 4 and  
the acidic treatment fluid is at least partially added in a  
pressurized steam treatment vessel, at a pressure in the  
25 vessel that exceeds that of a surrounding atmosphere by at  
least 0.5 bar.
3. (Previously presented) The method according to claim 1  
wherein the acidic fluid has a pH that does not exceed 4 and  
30 the acidic treatment fluid is partially added at least in a  
vessel at atmospheric pressure or at a slightly higher  
pressure, at a pressure in the vessel that exceeds that of a  
surrounding atmosphere by between 0 and 0.5 bar.

4. (Previously presented) The method according to claim 2 wherein a volume of the added acidic fluid relative to a volume of the chips does not exceed 2:1.

5 5. (Previously presented) The method according to claim 1 wherein the alkali impregnation fluid in which the heated and acidified chips are formed into a slurry is constituted by a sulphide-rich liquor.

10 6. (Previously presented) The method according to claim 5 wherein the alkali impregnation fluid is constituted by a mixture of at least one of a sulphide-rich white liquor, sulphide-rich black liquor, and/or sulphide-rich green liquor, and the alkali impregnation fluid has a molarity of  $\text{HS}^-$  that  
15 exceeds 0.15 mol/liter.

7. (Previously presented) The method according to claim 6 wherein the alkali impregnation fluid has a molarity of NaOH that does not exceed 0.75 mol/liter.

20 8. (Previously presented) The method according to claim 1 wherein the heating by steam of the chips together with the added acidic fluid takes place during a period of 1-20 minutes and at a temperature in a range of 80-120°C.

25